



CLIENT:

Company:	Global Syn-Turf
Address:	5960 Inglewood Dr Suite 150
	Pleasanton, CA 94588

TEST MATERIAL:

Date Material Received:	June 5, 2023
Material Type:	Synthetic Turf
Material Condition:	Excellent, New
Turf Identification:	Premier Cut
Infill 1:	1.5 lbs/ft ² Silica Sand
Pad System:	

TESTING METHODS REQUESTED:

<i>Testing Services Inc. was instructed by the client to test for the following...</i>			
Standard:	ASTM D2859	Test Method:	Standard Test Method for Ignition Characteristics of Finished Textile Pile Yarn Floorcoverings

SAMPLING PLAN:

Sampling Date:	6/5/2023
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST SCOPE:

This test method provides a method of determining the flammability characteristics of textile products when exposed to an ignition source in a laboratory environment. Eight specimens were taken from the sample lot, 230mm X 230mm, and preconditioned in an air circulating oven @ 150°C for 2 hours. After removal from the oven, the specimens are placed into a desiccator for 1 hour prior to performing the test. Each specimen was then placed into the test chamber floor with the pile surface up and a steel frame, 230mm X 230mm with 200mm diameter hole, placed on top of the specimen. A methenamine tablet was placed centrally onto the pile surface. The pill was ignited using a lighted match, with the ignition flame and propagated flame allowed to self-extinguish.

CRITERIA:

The specimen passes, if the charred portion of the test specimen, did not extend to within 25mm (1") of the diameter hole of the steel frame. The U.S. Consumer Product Safety Commission requires that at least seven of the eight specimens pass the test for acceptance as meeting the standard.

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT	
ASTM D2859-16	Ignition Characteristics of Textile Floor Coverings (Pill Test)	8 out of 8 Pass	Passes, U.S. CPSC 16CFR 1630 (FF1-70), Carpets & Rugs

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Erle Miles, III, Lab Director, Testing Services (TSI) LLC

TSI Accreditation: Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology; ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0.



Testing Services (TSI) LLC
 817 Showalter Avenue
 PO Box 1343
 Dalton, GA 30721